

## Type

Solvent-free 2-component decorative self leveling floor based on special, non-yellowing polyurethane resins.

## Applications

Strizo PU 50 NV is used on stable substrates in areas that require user comfort and an aesthetic effect.

As Strizo PU 50 NV does not turn yellow over time, it allows a transparent sealing.

The floor can be scattered with deco flakes when still wet. In short, the ideal floor system for use in shops, schools and homes.

## Packaging

Units of 20 kg each.

### Technical specifications

Colour	: high-gloss, colour category 1
(other colours available on request)	
Density	: 1.5 kg/l
Compression strength	: > 35 N/mm <sup>2</sup>
Shore D	: approx. 50°
Processing time	: 30 min. at 20°C
Curing time	: can be walked on after 16 hrs.;
full	chemical curing after 2 days at
20°C	
Recommended thickness	: 2–3 mm
Handling temperature	: min. +13°C – max. +30°C
Shelf life	: 12 months at room temperature



## Application instructions

To be applied in accordance with Comosil application instructions for Strizo PU 50 NV floors.

## Composition

- Strizo EP 110
- Strizo PU 50 NV
- Strizo PU 390

## Properties

- Solvent-free
- Does not turn yellow
- Extremely comfortable
- Seamless and aesthetic

### Safety

See Strizo PU 50 NV Safety Info Sheet

The data above has been gathered from the existing literature with the utmost care.  
Comosil B.V. does not accept any liability for damage of whatever nature or size arising from the use of this data.

1 September 2005